

UNCLASSIFIED

AD

434592

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA

Reproduced From
Best Available Copy

19990708209



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

RPL-TDR-64-38

**A COMPATIBILITY EVALUATION OF PLASTIC MEMBRANE FILTERS
WITH LIQUID PROPELLANTS AND SOLVENTS**

TECHNICAL DOCUMENTARY REPORT NO. RPL-TDR-64-38

FEBRUARY 1964

**AIR FORCE ROCKET PROPULSION LABORATORY
RESEARCH AND TECHNOLOGY DIVISION
AIR FORCE SYSTEMS COMMAND
EDWARDS, CALIFORNIA**

434592

CATALOGED BY JDU
AS AD. NO. —

434592

RPL-TDR-64-38

A COMPATIBILITY EVALUATION OF PLASTIC MEMBRANE FILTERS
WITH LIQUID PROPELLANTS AND SOLVENTS

TECHNICAL DOCUMENTARY REPORT NO. RPL-TDR-64-38

February 1964

AIR FORCE ROCKET PROPULSION LABORATORY
RESEARCH AND TECHNOLOGY DIVISION
AIR FORCE SYSTEMS COMMAND
Edwards, California

RPL-TDR-64-38
February 1964

**A COMPATIBILITY EVALUATION OF PLASTIC MEMBRANE FILTERS
WITH LIQUID PROPELLANTS AND SOLVENTS**

By

ROBERT A. BIGGERS

This report has been reviewed and approved.


J. M. SILK
Colonel, USAF
Director, Air Force Rocket Propulsion Laboratory

ABSTRACT

Data is presented to show the compatibility of polyethylene filter membranes with eleven propellants and eight solvents. More than 300 tests were conducted at ambient temperatures for periods up to 52 hours. The filters tested are satisfactory for use in the gravimetric determination of particulate matter in most liquid propellants.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	v
INTRODUCTION	1
TEST PROGRAM	1
Description of Item Tested	1
Description of Test Apparatus	1
Propellants Used	2
Solvents Used	2
Number of Tests	3
Operational Procedure	3
Test Results	4
Effect of Solvents	4
CONCLUSIONS	7
BIBLIOGRAPHY.....	8

LIST OF TABLES

I	Compatibility of Membranes with MMH and IRFNA	5
II	Compatibility of Membranes with Solvents	6

APPENDIX

A	- Compatibility of Prototype Membranes	A-1
B	- Compatibility of Intermediate Membranes	B-1
C	- Compatibility of Production Membranes	C-1

A COMPATIBILITY EVALUATION OF PLASTIC MEMBRANE FILTERS WITH LIQUID PROPELLANTS AND SOLVENTS

INTRODUCTION.

Particle contamination and procedures for measuring particulates have long been serious problems in rocket propulsion systems. To better understand and resolve some of the problems in this area, two principal contracts were awarded: Air Products⁽¹⁾ for measuring contaminants in cryogenics, and the Fluor Corporation⁽²⁻⁵⁾ to develop methods for sampling and laboratory analysis. One of the procedures recommended by the contractors involved the use of the cellulose membrane filter. However, the cellulose membrane is not compatible with most storable propellants and often disintegrates when used with cryogenics.

A membrane filter was developed by the Millipore Corporation⁽⁶⁾ to replace the cellulose filter. This new filter is relatively inert to all missile propellants, has good retention efficiency, provides surface filtration, has uniform pore size in the 1-10 micron range, and the weight of an individual membrane is less than 100 milligrams.

The purpose of this report is to present the data obtained in the evaluation of the plastic membrane filter with propellants.

TEST PROGRAM.

Description of the Item Tested: The membrane filters tested were polyethylene, 47 mm in diameter, approximately 0.3 mm in thickness, and vary in weight 60-100 mg. Two pore sizes were tested: 1.5 and 10 microns.

Description of Test Apparatus: The test apparatus used in the filter evaluation was composed of standard items:

1. All-glass filter apparatus -- 47 mm pyrex filter holder with tapered ground glass joint between holder base and flask, holding clamp, 300 ml funnel and 1-liter ground joint pyrex flask.

2. Two-inch diameter glass petri dishes.
3. Stainless steel water aspirator.
4. Analytical balance with a minimum sensitivity of 0.05 mg.
5. Vacuum oven.

Propellants Used: All propellants used for testing purposes were taken from storage drums or tanks. The propellants conformed to the requirements listed in the following military specifications:

1. Propellant, Hydrazine - unsDimethylhydrazine (MIL-P-27402).
2. Propellant, Monomethylhydrazine (MIL-P-27404).
3. Propellant, unsDimethylhydrazine (MIL-P-25604A).
4. Propellant, Hydrazine (MIL-P-26536A).
5. Propellant, Hydrogen Peroxide (MIL-P-16005D).
6. Propellant, Nitrogen Tetroxide (MIL-P-26539).
7. Propellant, JP-4/UDMH (MIL-P-26694).
8. Rocket Fuel RP-1 (MIL-P-25576B).
9. Propellant, Nitric Acid (MIL-P-7254 Type III).
10. Propellant, Nitrogen, Pressurizing Agent, Type II (MIL-P-27401B).
11. Propellant, Normal Propyl-Nitrate (MIL-N-8722A).

Solvents Used: A limited number of solvents were used to evaluate the membrane filters. The following solvents were selected on the basis of their compatibility with various propellants:

1. Water
2. Acetone
3. Methylene chloride
4. Petroleum Ether
5. Isopropyl Alcohol
6. Ethyl Alcohol
7. Carbon Tetrachloride
8. Chloroform

Number of Tests: Approximately 111 individual tests were conducted on the polyethylene membrane filters. The membranes are categorized as follows: the prototype, the intermediate, and the production item. Over 130 tests were conducted on the prototype membranes, 110 tests on the intermediate, and 90 tests on the production item. The 1.5 micron and 10 micron membranes are grouped together, although they were tested separately. The manufacturing process differed slightly for filters of the two pore sizes, but no distinct difference was noted regarding each membrane's compatibility with the propellants.

Operational Procedure: Prior to each sample test, all items of the filtration apparatus and sample bottle were cleaned with detergent, rinsed twice with distilled water, rinsed twice with isopropyl alcohol, and allowed to dry. Finally, the apparatus was rinsed twice with filtered petroleum ether and allowed to dry until the petroleum ether vapors completely disappeared.

One 10-micron (or 1.5 micron) solvent resistant filter disc was weighed to the nearest 0.1 mg. Forceps were used to place the filter disc in a covered petri dish. An additional filter was weighed and set aside as the control filter.

The control filter disc was removed from the petri dish with forceps and the filter placed on the filter holder base. The tared filter disc was placed directly on top of the control filter. The filter holder funnel was clamped to the base, the vacuum system turned on, and the sample filtered in 200-ml portions. Next, the sample bottle was rinsed with filtered solvent (compatible with the propellant). The sides of the funnel and filter disc were rinsed by pouring the sample bottle rinsings into the funnel. The funnel was disconnected from the base and the filter disc edges rinsed carefully with a jet of filtered solvent to accumulate the particulate residue toward the center of the disc while evacuation continued. The vacuum was released. Forceps were used to place the filter disc in the covered petri dish. The control filter disc was placed in an additional covered petri dish. The dishes, covers ajar, were placed in a vacuum oven at 70°C for 30 minutes. The filter discs were then reweighed at ambient temperature to the nearest 0.1mg.

An additional procedure was used to evaluate the membranes. The tared test membrane and 100 ml of propellant were placed in a closed bottle, mechanically shaken for periods of 15 minutes to 52 hours, and reweighed.

Test Results: The prototype membrane filters were not compatible with most of the propellants. Also, they were unsatisfactory for gravimetric use, i. e., a 100-mg. filter disc lost 10% of its total weight when subjected to red fuming nitric acid (RFNA) for 50 hours in a shaker. These same filters lost 4% of their total weight on direct filtration of 200 ml of RFNA. As the formulation of polyethylene improved, the chemical attack on the membranes by the propellants was less severe.

During the testing of the prototype filters, RFNA and monomethylhydrazine (MMH) were found to be the most incompatible of the propellants used. MMH and RFNA were used almost exclusively to evaluate the intermediate and production item membranes. Typical test results with these two propellants are shown in Table I.

The intermediate filters lost approximately two mg (100 mg disc) with the long-duration RFNA tests, and the production item lost one mg. when subjected to the same test. (A complete list of data is included in the Appendix.)

No membrane completely failed. Swelling occurred with the hydrocarbon fuels, but the membranes showed no loss of elasticity and no distortion with any of the other propellants.

Effect of Solvents: The solvents were more compatible with the production membranes than were the propellants. The results of a 16-hour shaker test are reported in Table II.

The solvent extraction is of little importance, since the initial weight loss is accomplished by the propellant filtration. The tests indicate that the maximum weight loss of membranes occurs in the initial contact with the propellant.

TABLE I
COMPATIBILITY OF MEMBRANES WITH MMH AND RFNA

Control Membrane No.	Initial wt. -mg.	Run #1 Prop. Filtered	Weight Loss mg.	Run #2 Prop. Filtered	Weight Loss mg.	Run #3 Prop. Filtered	Weight Loss mg.
Proto #2	106.7	200 ml. MMH	9.1	200 ml. MMH	1.5	200 ml. MMH	0.3
Proto #10	98.2	200 ml. RFNA	10.4	200 ml. RFNA	0.8	200 ml. RFNA	0.0
Inter. #1	76.5	200 ml. MMH	0.4	200 ml. MMH	0.4	200 ml. MMH	0.1
Inter. #2	77.6	200 ml. RFNA	0.5	200 ml. RFNA	0.1	200 ml. RFNA	0.0
Prod. #1	95.3	500 ml. MMH	0.1	500 ml. MMH	0.0	500 ml. MMH	0.0
Prod. #7	99.3	500 ml. RFNA	0.7	500 ml. RFNA	0.4	500 ml. RFNA	0.0

TABLE II
COMPATIBILITY OF MEMBRANES WITH SOLVENTS

<u>Control Membrane No.</u>	<u>Initial Weight mg</u>	<u>Solvent in Shaker</u>	<u>Weight Loss mg.</u>
Sol. 1	102.1	Methylene Chloride	0.5
Sol. 11	98.0	Petroleum Ether	0.5
Sol. 13	99.7	Acetone	0.3
Sol. 15	101.4	Chloroform	0.9
Sol. 17	100.1	Carbontetrachloride	0.9
Sol. 19	99.1	Isopropyl Alcohol	0.1
Sol. 21	97.5	Ethyl Alcohol	0.1

CONCLUSIONS.

The production membranes, now marketed as Type OS and OH filters, are resistant to most propellants. The membranes are compatible with all of the solvents tested. The membranes may not be used for gravimetric analysis with hydrocarbon-type fuels.

The membrane filters are inexpensive, disposable, easy to use, and have excellent chemical resistance.

BIBLIOGRAPHY

1. Foster, R.H. , "Study of Liquid Contamination," Air Products and Chemicals, Inc. , SSD-TDR-62-8, May 1961.
- 2-5. Dutch, Paul H. , MacInnes, W.F. , "Development of Sampling Techniques and Particulate Matter Analysis," the Fluor Corporation, Ltd. , AFFTC-TR 60-44, 60-45, 60-46, 60-47, November 1959.
6. "Detection and Analysis of Contamination," Millipore Filter Corporation ADM-30, November 1962.

APPENDIX A

COMPATIBILITY OF PROTOTYPE MEMBRANES

COMPATIBILITY OF PROTOTYPE MEMBRANES

Control Membrane No.	Initial Wt. in mgs.	Run #1 Prop. Test	Wt. Loss mg.	Run #2 Prop. Test	Wt. Loss mg.	Run #3 Prop. Test	Wt. Loss mg.	Run #4 Prop. Test	Wt. Loss mg.	Run #5 Prop. Test	Wt. Loss mg.	Percent Total Loss
1	107.0	200 ml. UDMH/ N ₂ H ₄	9.1	200 ml N ₂ H ₄	1.7	200 ml. RFNA	0.3	200 ml. N ₂ H ₄	0.5	200 ml. N ₂ H ₄	0.0	10.8
2	106.7	200 ml. MTH	9.1	200 ml. MTH	1.5	200 ml. MTH	0.3	200 ml. MTH	0.1	200 ml. MTH	0.0	10.3
3	82.6	24-hr Shake N ₂ H ₄	9.4	200 ml. N ₂ H ₄	0.4	200 ml. N ₂ H ₄	0.1	200 ml. N ₂ H ₄	0.0	--	--	12.0
4	90.8	24-hr. Shake UDMH/ N ₂ H ₄	8.3	200 ml. N ₂ H ₄	0.5	200 ml. N ₂ H ₄	0.0	200 ml. N ₂ H ₄	0.0	--	--	9.7
5	99.2	52-hr Shake N ₂ H ₄	11.5	200 ml. N ₂ H ₄	0.0	200 ml JP-X	0.0	200 ml. MTH	0.4	200 ml. MTH	0.0	12.0
6	86.1	52-hr. Shake N ₂ H ₄	7.5	200 ml. N ₂ H ₄	0.0	200 ml. JP-X	0.0	200 ml. MTH	0.3	200 ml. MTH	0.1	9.1
7	91.0	52-hr. Shake N ₂ H ₄	9.0	200 ml. H ₂ O ₂ (90%)	0.0	200 ml. MTH	0.3	200 ml. MTH	0.1	200 ml. MTH	0.0	10.3
8	85.9	52-hr. Shake N ₂ H ₄	7.7	200 ml RFNA	0.0	200 ml. N-Propyl- N	0.0	200 ml. MTH	0.2	200 ml. MTH	0.1	9.2
9	(52-hr 97.4	Shake RFNA	10.2	200 ml. N ₂ H ₄	0.2	200 ml. MTH	0.1	200 ml. MTH	0.0	--	--	10.8

COMPATIBILITY OF PROTOTYPE MEMBRANES (Cont'd)

Control Membrane No.	Initial Wt. in mgs.	Run #1 Prop. Test	Wt. Loss mg.	Run #2		Run #3		Run #4		Run #5		Percent Total Loss	
				Prop. Test	Wt. Loss mg.	Prop. Test	Wt. Loss mg.	Prop. Test	Wt. Loss mg.	Prop. Test	Wt. Loss mg.		
10	98.2	200 ml. RFNA	10.4	200 ml. RFNA	0.8	200 ml. RFNA	0.0	200 ml. MTH	0.0	---	---	11.4	
11	99.6	50-hr. Shake RFNA	10.8	18-hr. RFNA	0.6	4-hr. RFNA	0.0	200 ml. MTH	0.0	---	---	11.4	
12	85.6	42-hr. Shake N_2H_4	7.0	200 ml. N_2H_4	0.5	200 ml. MTH	0.0	---	---	---	---	8.8	
13	88.4	50-hr. Shake N_2H_4	7.6	18-hr. Shake N_2H_4	0.1	4-hr. Shake N_2H_4	0.2	200 ml. MTH	0.0	---	---	8.9	
14	85.1	50-hr. Shake N_2H_4	7.0	18-hr. Shake N_2H_4	0.5	4-hr. Shake N_2H_4	0.2	200 ml. MTH	0.0	---	---	9.0	
15	80.2	18-hr. Shake N_2H_4	5.3	6-hr. Shake N_2H_4	0.3	18-hr. Shake N_2H_4	0.0	200 ml. MTH	0.0	200 ml. RFNA	0.0	7.0	
16	79.2	18-hr. Shake UDMH/ N_2H_4	4.3	6-hr. Shake N_2H_4	0.1	18-hr. Shake N_2H_4	0.2	200 ml. MTH	0.0	100 ml. MTH	0.0	5.8	
17	86.7	Heat 170°F	0.2	100 ml. H_2O / Acetone	0.2	200 ml. Conc. HF	9.0	200 ml. MTH	2.0	200 ml. MTH	0.0	6.2	
18	78.0	1.5 hr. Shake N_2H_4	4.3	0.5 hr. Shake N_2H_4	0.5	1-hr. Shake N_2H_4	0.1	200 ml. MTH	0.0	---	---	6.3	

COMPATIBILITY OF PROTOTYPE MEMBRANES (Cont'd)

Control Initial Membrane No.	Run #1 Prop. Test	Wt. Loss mg.	Run #2 Prop. Test	Wt. Loss mg.	Run #3 Prop. Test	Wt. Loss mg.	Run #4 Prop. Test	Wt. Loss mg.	Run #5 Prop. Test	Wt. Loss mg.	Percent Total Loss
19	82.7 7.5-hr. Shake RFNA	5.9	0.5-hr. Shake RFNA	0.1	1-hr. Shake RFNA	0.1	200 ml. MH	0.0	--	--	7.4
20	84.2 200 ml. 90% H ₂ O ₂	3.9	--	--	--	--	--	--	--	--	4.6
21	78.4 200 ml. JP-X	0.7	--	--	--	--	--	--	--	--	0.9
22	98.3 200 ml. MH	6.9	--	--	--	--	--	--	--	--	7.0
23	83.5 200 ml. MH	3.5	--	--	--	--	--	--	--	--	4.2
24	78.4 200 ml. MH	4.5	200 ml. RFNA	0.6	--	--	--	--	--	--	6.0
25	89.6 2000 ml. Liq. N ₂	0.1	--	--	--	--	--	--	--	--	0.1
26	82.8 0.1-hr. RFNA	5.0	200 ml. MH	0.7	200 ml. MH	0.1	--	--	--	--	7.0
27	73.5 0.2-hr. RFNA	3.0	200 ml. MH	0.6	200 ml. MH	0.0	--	--	--	--	4.9
28	92.5 0.5-hr. Shake N ₂ H ₄	8.2	200 ml. MH	0.5	200 ml. MH	0.0	--	--	--	--	9.4
29	83.6 0.5-hr. Shake UDMH/N ₂ H ₄	5.9	200 ml. MH	0.5	200 ml. MH	0.0	--	--	--	--	7.7
30	98.6 0.5-hr. Shake RFNA	9.0	0.5 hr. Shake RFNA	0.9	200 ml. MH	0.6	200 ml. MH	0.0	--	--	10.6

COMPATIBILITY OF PROTOTYPE MEMBRANES (Cont'd)

Control Membrane No.	Initial Wt. in mgs.	Run #1 Prop. Test	Wt. Loss mg.	Run #2 Prop. Test	Wt. Loss mg.	Run #3 Prop. Test	Wt. Loss mg.	Run #4 Prop. Test	Wt. Loss mg.	Run #5 Prop. Test	Wt. Loss mg.	Percent Total Loss
31	91.5	0.5-hr. Shake RFNA	2.0	0.5-hr. Shake RFNA	1.0	200 ml. MMH	5.2	200 ml. MMH	0.0	--	--	9.0
32	64.4	24-hr. Shake MMH	2.2	48-hr. Shake MMH	0.1	--	--	--	--	--	--	3.6
33	72.9	"	3.8	"	0.1	--	--	--	--	--	--	5.3
34	82.8	"	6.3	"	0.1	--	--	--	--	--	--	7.7
35	95.1	"	10.0	"	0.3	--	--	--	--	--	--	10.8
36	61.9	"	1.9	"	0.2	--	--	--	--	--	--	3.4
37	71.0	"	3.3	"	0.1	--	--	--	--	--	--	4.8

APPENDIX B

COMPATIBILITY OF INTERMEDIATE MEMBRANES

COMPATIBILITY OF INTERMEDIATE MEMBRANES

Control Membrane No.	Initial Wt. in mgs.	Run #1 Prop. Test	Wt. Loss mg.	Run #2 Prop. Test	Wt. Loss mg.	Run #3 Prop. Test	Wt. Loss mg.	Run #4 Prop. Test	Wt. Loss mg.	Run #5 Prop. Test	Wt. Loss mg.	Percent Total Loss
1	76.5	200 ml. MMH	0.4	200 ml. MMH	0.4	200 ml. MMH	0.1	—	—	—	—	1.2
2	77.6	200 ml. RFNA	0.5	200 ml. RFNA	0.1	200 ml. RFNA	0.0	—	—	—	—	0.7
3	79.6	3-hr. Shake N ₂ H ₄	0.7	200 ml. MMH	0.1	200 ml. MMH	0.0	—	—	—	—	1.0
4	78.3	3-hr. Shake RFNA	1.0	200 ml. MMH	0.1	200 ml. MMH	0.0	—	—	—	—	1.4
5	79.8	200 ml. MMH	0.7	—	—	—	—	—	—	—	—	0.9
6	72.0	"	0.6	—	—	—	—	—	—	—	—	0.8
7	76.2	"	0.6	—	—	—	—	—	—	—	—	0.8
8	78.7	200 ml. N ₂ H ₄	0.6	200 ml. N ₂ H ₄	0.3	—	—	—	—	—	—	1.1
9	68.2	"	0.6	"	0.2	—	—	—	—	—	—	1.2
10	71.7	"	0.6	"	0.1	—	—	—	—	—	—	1.0
11	75.0	200 ml. UDMH/N ₂ H ₄	0.6	300 ml. N ₂ O ₄	0.1	200 ml. MMH	0.2	200 ml. MMH	0.0	—	—	1.2
12	79.7	"	0.6	"	0.1	"	0.2	"	0.0	—	—	1.1
13	89.5	200 ml. N ₂ H ₄	0.7	200 ml. N ₂ H ₄	0.1	"	0.5	"	0.6	0.1-hr. Shake MMH	0.3	2.5
14	91.5	"	0.7	"	0.2	"	0.5	"	0.5	"	0.5	2.6
15	90.9	"	0.7	"	0.1	"	0.4	"	0.6	"	0.5	2.5

COMPATIBILITY OF INTERMEDIATE MEMBRANES (Cont'd)

Control Membrane No.	Initial Wt. in mg.	Run #1 Prop. Test	Wt. Loss mg.	Run #2 Prop. Test	Wt. Loss mg.	Run #3 Prop. Test	Wt. Loss mg.	Run #4 Prop. Test	Wt. Loss mg.	Run #5 Prop. Test	Wt. Loss mg.	Percent Total Loss
16	98.0	3-hr. Shake RFNA	0.8	200 ml. MMH	1.3	200 ml. MMH	0.1	200 ml. MMH	0.0	—	—	2.2
17	87.5	"	1.0	"	0.9	"	0.1	"	0.0	—	—	2.3
18	74.5	20-hr. Shake MMH	1.3	200 ml. MMH	0.0	—	—	—	—	—	—	1.7
19	78.0	"	1.6	"	0.0	—	—	—	—	—	—	2.1
20	68.8	800 ml. MMH	0.5	800 ml. MMH	0.0	—	—	—	—	—	—	0.7
21	67.8	"	0.5	"	0.0	—	—	—	—	—	—	0.8
22	59.9	500 ml. UDMH/N ₂ H ₄	0.3	500 ml. UDMH/N ₂ H ₄	0.3	—	—	—	—	—	—	1.0
23	58.6	"	0.3	"	0.3	—	—	—	—	—	—	1.0
24	61.9	20-hr. Shake MMH	0.6	400 ml. MMH	0.0	—	—	—	—	—	—	1.0
25	61.4	500 ml. MMH	0.5	500 ml. MMH	0.0	—	—	—	—	—	—	0.7
26	62.4	500 ml. UDMH/N ₂ H ₄	0.1	500 ml. UDMH/N ₂ H ₄	0.4	500 ml. UDMH/N ₂ H ₄	0.1	400 ml. MMH	0.0	—	—	1.0
27	102.8	2-hr. Shake MMH	0.3	18-hr. Shake MMH	0.0	—	—	—	—	—	—	0.3
28	101.0	"	0.3	"	0.0	—	—	—	—	—	—	0.3
29	97.4	800 ml. MMH	0.3	800 ml. MMH	0.0	—	—	—	—	—	—	0.3
30	99.4	"	0.4	"	0.0	—	—	—	—	—	—	0.4

COMPATIBILITY OF INTERMEDIATE MEMBRANES (Cont'd)

Control Membrane No.	Initial Wt. in mgs.	Run #1 Prop. Test	Wt. Loss mg.	Run #2 Prop. Test	Wt. Loss mg.	Run #3 Prop. Test	Wt. Loss mg.	Run #4 Prop. Test	Wt. Loss mg.	Run #5 Prop. Test	Wt. Loss mg.	Percent Total Loss
31	97.0	500 ml. UDMH/N ₂ H ₄	0.2	500 ml. UDMH/N ₂ H ₄	0.0	800 ml. MMH	0.1	—	—	—	—	0.3
32	96.2	500 ml. UDMH/N ₂ H ₄	0.1	500 ml. UDMH/N ₂ H ₄	0.0	800 ml. MMH	0.2	—	—	—	—	0.3
33	68.9	24-hr. Shake MMH	0.5	—	—	—	—	—	—	—	—	0.7
34	73.3	"	1.3	—	—	—	—	—	—	—	—	1.8
35	75.0	"	1.2	—	—	—	—	—	—	—	—	1.6
36	98.9	"	0.3	—	—	—	—	—	—	—	—	0.3
37	96.7	"	0.3	—	—	—	—	—	—	—	—	0.3
38	93.7	170-hr. Shake MMH	0.5	—	—	—	—	—	—	—	—	0.5
39	94.8	"	0.7	—	—	—	—	—	—	—	—	0.7
40	95.6	"	0.8	—	—	—	—	—	—	—	—	0.8
41	96.5	"	0.9	—	—	—	—	—	—	—	—	0.9
42	97.0	"	1.0	—	—	—	—	—	—	—	—	1.0
43	99.8	"	0.8	—	—	—	—	—	—	—	—	0.8
44	99.2	"	0.9	—	—	—	—	—	—	—	—	0.9
45	97.6	"	1.1	—	—	—	—	—	—	—	—	1.1

APPENDIX C

COMPATIBILITY OF PRODUCTION MEMBRANES (PROPELLANT TEST & SOLVENT TEST)

COMPATIBILITY OF PRODUCTION MEMBRANES

Control Membrane No.	Initial Wt. in mgs.	Run #1 Prop. Test	Wt. Loss mg.	Run #2 Prop. Test	Wt. Loss mg.	Run #3 Prop. Test	Wt. Loss mg.	Run #4 Prop. Test	Wt. Loss mg.	Run #5 Prop. Test	Wt. Loss mg.	Percent Total Loss
1	95.3	500 ml. MMH	0.1	500 ml. MMH	0.0	500 ml. MMH	0.0	500 ml. MMH	0.0	—	—	0.1
2	95.1	"	0.0	"	0.0	"	0.0	"	0.0	—	—	0.0
3	96.0	"	0.0	"	0.0	"	0.0	"	0.0	—	—	0.0
4	94.5	500 ml. UDMH/N ₂ H ₄	0.1	500 ml. UDMH/N ₂ H ₄	0.0	500 ml. UDMH/N ₂ H ₄	0.0	500 ml. UDMH/N ₂ H ₄	0.0	—	—	0.1
5	96.9	"	0.1	"	0.0	"	0.0	"	0.0	—	—	0.1
6	95.4	"	0.0	"	0.0	"	0.0	"	0.0	—	—	0.1
7	99.3	500 ml. RFNA	0.7	500 ml. RFNA	0.2	500 ml. RFNA	0.3	500 ml. RFNA	0.0	—	—	1.2
8	99.3	"	0.6	"	0.3	"	0.3	"	0.0	—	—	1.2
9	100.5	"	0.7	"	0.2	"	0.4	"	0.0	—	—	1.3
10	101.8	"	0.6	"	0.2	"	0.4	"	0.0	—	—	1.2
11	101.5	100 ml. CH ₂ Cl ₂	0.4	100 ml. Pet. Ether	0.0	100 ml. CH ₂ Cl ₂	0.2	100 ml. RFNA	0.3	100 ml. RFNA	0.0	0.9
12	100.7	"	0.4	"	0.1	"	0.1	"	0.3	"	0.1	1.0
13	99.5	"	0.3	"	0.1	"	0.1	"	0.3	"	0.1	0.9
14	98.8	"	0.3	"	0.1	"	0.2	"	0.3	"	0.1	1.0
15	96.8	70-hr. Shake RFNA	0.6	4-hr. Shake RFNA	0.1	—	—	—	—	—	—	0.7
16	97.0	"	0.6	"	0.1	—	—	—	—	—	—	0.7
17	77.5	"	0.4	"	0.1	—	—	—	—	—	—	0.5

COMPATIBILITY OF PRODUCTION MEMBRANES (Cont'd)

Control Membrane No.	Initial Wt. in Egs.	Run #1 Prop. Test	Wt. Loss mg.	Run #2 Prop. Test	Wt. Loss mg.	Run #3 Prop. Test	Wt. Loss mg.	Run #4 Prop. Test	Wt. Loss mg.	Run #5 Prop. Test	Wt. Loss mg.	Percent Total Loss
18	103.4	28-hr. Shake N ₂ O ₄ - .08% H ₂ O	0.1	--	--	--	--	--	--	--	--	0.1
19	103.3	"	0.2	--	--	--	--	--	--	--	--	0.2
20	103.7	28-hr. Shake N ₂ O ₄ - .21% H ₂ O	0.1	--	--	--	--	--	--	--	--	0.1
21	100.5	"	0.1	--	--	--	--	--	--	--	--	0.1
22	104.6	28-hr. N ₂ O ₄ - .36% H ₂ O	0.1	--	--	--	--	--	--	--	--	0.1
23	103.5	"	0.2	--	--	--	--	--	--	--	--	0.2
24	101.2	180-hr. N ₂ O ₄ - .26% H ₂ O	0.2	--	--	--	--	--	--	--	--	0.2
25	103.8	"	0.2	--	--	--	--	--	--	--	--	0.2

	Run #1 Solvent Test	Run #2 Solvent Test	Run #3 Solvent Test	Run #4 Solvent Test	Run #5 Solvent Test
1	102.1 24-hr. CH ₂ Cl ₂	0.5 60-hr. RFNA	0.6 4-hr. RFNA	0.0	--
2	103.1 "	0.5 "	0.6 "	0.0	--
3	101.7 "	0.7 "	0.5 "	0.0	--
4	102.1 "	0.5 "	0.6 "	0.0	--
5	104.3 "	0.6 "	0.6 "	0.0	--

COMPATIBILITY OF PRODUCTION MEMBRANES (Cont'd)

Control Membrane No.	Initial Wt. in mg.	Run #1 Solvent Test	Wt. Loss mg.	Run #2 Solvent Test	Wt. Loss mg.	Run #3 Solvent Test	Wt. Loss mg.	Run #4 Solvent Test	Wt. Loss mg.	Run #5 Solvent Test	Wt. Loss mg.	Percent Total Loss
6	100.1	100 ml. CH_2Cl_2	0.3	100 ml. $\text{CH}_3\text{CHOHCH}_3$	0.0	100 ml. Pet. Ether	0.0	100 ml. CH_2Cl_2	0.1	100 ml. CH_2Cl_2	0.0	0.4
7	101.5	"	0.4	"	0.0	"	0.0	"	0.1	"	0.1	0.6
8	100.7	"	0.4	"	0.0	"	0.1	"	0.1	"	0.0	0.6
9	99.5	"	0.3	"	0.0	"	0.1	"	0.1	"	0.0	0.5
10	98.8	"	0.3	"	0.0	"	0.1	"	0.3	"	0.0	0.6
11	98.0	6-hr. Shaker	0.5	—	—	—	—	—	—	—	—	0.5
12	98.2	Pet. Ether	0.6	—	—	—	—	—	—	—	—	0.6
13	99.7	16-hr. CH_3COCH_3	0.3	—	—	—	—	—	—	—	—	0.3
14	100.7	"	0.3	—	—	—	—	—	—	—	—	0.3
15	101.4	16-hr. CHCl_3	0.9	—	—	—	—	—	—	—	—	0.9
16	101.3	"	0.9	—	—	—	—	—	—	—	—	0.9
17	100.1	16-hr. CCl_4	0.9	—	—	—	—	—	—	—	—	0.9
18	99.8	"	1.0	—	—	—	—	—	—	—	—	1.0
19	99.1	16-hr. $\text{CH}_3\text{CHOHCH}_3$	0.1	—	—	—	—	—	—	—	—	0.1
20	98.9	"	0.1	—	—	—	—	—	—	—	—	0.1
21	97.5	16-hr. $\text{CH}_3\text{CH}_2\text{OH}$	0.1	—	—	—	—	—	—	—	—	0.1
22	95.4	"	0.2	—	—	—	—	—	—	—	—	0.2

COMPATIBILITY OF PRODUCTION MEMBRANES (Cont'd)

Control Membrane No.	Initial Wt. in mg.	Run #1 Solvent Test	Wt. Loss mg.	Run #2 Solvent Test	Wt. Loss mg.	Run #3 Solvent Test	Wt. Loss mg.	Run #4 Solvent Test	Wt. Loss mg.	Run #5 Solvent Test	Wt. Loss mg.	Percent Total Loss
23	102.1	24-hr. Shake CH ₂ Cl ₂	0.5	70-hr. Shake RFNA	0.6	4-hr. Shake RFNA	0.0	--	--	--	--	1.1
24	103.1	"	0.5	"	0.6	"	0.1	--	--	--	--	1.1
25	101.7	"	0.7	"	0.6	"	0.0	--	--	--	--	1.3
26	102.1	"	0.5	"	0.6	"	0.0	--	--	--	--	1.2
27	104.3	"	0.6	"	0.6	"	0.0	--	--	--	--	1.2

RPL-TDR-64-38
DISTRIBUTION LIST

U. S. Department of the Interior Bureau of Mines 4800 Forbes Avenue Pittsburgh, Pennsylvania 15213 Attn: M. M. Dolinar, Repts Librarian Explosives Research Center	1	Nat'l Aeronautics & Space Admin Washington, D. C. 20546 Attn: Office of Technical Information & Education Programs, Code ETL	1
		Scientific & Tech. Info. Facility P. O. Box 5700	2
Central Intelligence Agency 2430 E Street, N. W. Washington, D. C. 20505 Attn: OCD, Standard Dist	1	Bethesda, Maryland 20014 Attn: NASA Representative	
Office of the Director of Defense Research and Engineering Washington, D. C. 20301 Attn: W. E. Sheehan, Office of Asst. Dir. (Chemical Technology)	1	Nat'l Aeronautics & Space Admin. Washington, D. C. 20546 Attn: R. W. Ziem (RPS)	1
Nat'l Aeronautics & Space Admin. Lewis Research Center 21000 Brookpark Road Cleveland, Ohio 44135 Attn: Library	1	Nat'l Aeronautics & Space Admin. Goddard Space Flight Center Greenbelt, Maryland 20771 Attn: Library	1
		Defense Documentation Center Cameron Station Alexandria, Virginia 22314	20
Nat'l Aeronautics & Space Admin. Launch Operations Center Cocoa Beach, Florida 32931 Attn: Library	1	Air Force Systems Command Attn: SCTAP Andrews AFB Washington, D. C. 20331	1
Nat'l Aeronautics & Space Admin. Manned Spacecraft Center P. O. Box 1537 Houston, Texas 77001 Attn: Library		Arnold Eng. Development Center Attn: AEOIM Air Force Systems Command Tullahoma, Tennessee 37389	1
Nat'l Aeronautics & Space Admin. George C. Marshall Space Flight Center Huntsville, Alabama 35800 Attn: Library	1	AFRPL (RPR) Edwards, California 93523	1
		AFRPL (RPM) Edwards, California 93523	1
Nat'l Aeronautics & Space Admin. Langley Research Center Langley Air Force Base Virginia 23365 Attn: Library	3	AFRPL (RPCC) Edwards, California 93523	60

Distribution p. 2

AFFTC (FTAT-2) Edwards AFB, California 93523	1	Commanding Officer Picatinny Arsenal Liquid Rocket Propulsion Laboratory Dover, New Jersey 07801 Attn: Technical Library	1
Office of Research Analysis Attn: RRRT Holloman AFB, New Mexico 88330	1	U. S. Army Missile Command Redstone Scientific Info. Center Redstone Arsenal, Alabama 35808 Attn: Chief, Document Section	4
Air Force Missile Test Center Attn: MTBAT Patrick Air Force Base, Florida 32925	1	Commanding General White Sands Missile Range New Mexico 88002 Attn: Technical Library	1
Wright-Patterson AFB, Ohio 45433 Attn: AFML(MAAE)	1	Bureau of Naval Weapons Department of the Navy Washington, D. C. 20360 Attn: DLI-3	2
Commanding Officer Ballistic Research Laboratories Aberdeen Proving Ground, Maryland Attn: AMXBR-1 21005	1	Bureau of Naval Weapons Department of the Navy Washington D. C. 20360 Attn: RMMP-2	2
Commanding Officer Harry Diamond Laboratories Washington, D. C. 20438 Attn: AMXDO-TIB	1	Bureau of Naval Weapons Department of the Navy Washington, D. C. 20360 Attn: RMMP-3	1
Commanding Officer U. S. Army Research Office (Durham) Box CM, Duke Station Durham, North Carolina 27706	1	Bureau of Naval Weapons Department of the Navy Washington, D. C. 20360 Attn: RMMP-4	1
Commanding Officer U. S. Army Chemical Research & Development Laboratories Edgewood Arsenal, Maryland 21010 Attn: Chief, Physicochemical Research Division	1	Bureau of Naval Weapons Department of the Navy Washington, D. C. 20360 Attn: RRRF-6	1
Commanding Officer Frankford Arsenal Philadelphia, Pennsylvania 19137 Attn: Propellant & Explosives Section, 1331	1	Commander U. S. Naval Missile Center Point Mugu, California 93041 Attn: Technical Library	2

Distribution p. 3

Commander
U. S. Naval Ordnance Laboratory
White Oak
Silver Spring, Maryland 20910
Attn: Library

Commander
U. S. Naval Ordnance Test Station
China Lake, California 93557
Attn: Code 45

Commander (Code 753)
U. S. Naval Ordnance Test Station
China Lake, California 93557
Attn: Technical Library

Superintendent
U. S. Naval Postgraduate School
Naval Academy
Monterey, California

Commanding Officer
U. S. Naval Propellant Plant
Indian Head, Maryland 20640
Attn: Technical Library

Commanding Officer
Office of Naval Research
1030 E. Green Street
Pasadena, California 91101

Director (Code 6180)
U. S. Naval Research Lab.
Washington, D. C. 20390
Attn: H. W. Carhart

Director
Special Projects Office
Department of the Navy
Washington, D. C. 20360

Commanding Officer
U. S. Naval Underwater Ordnance Station
Newport Rhode Island 02844
Attn: W. W. Bartlett

Aerojet-General Corporation
P. O. Box 296
Azusa, California 91703
Attn: Librarian

2 Aerojet-General Corporation 1
11711 South Woodruff Avenue
Downey, California 90241
Attn: Florence Walsh, Librarian

Aerojet-General Corporation 3
5 P. O. Box 1947
Sacramento, California 95809
Attn: Technical Information Office

Aeronutronic Div. Philco Corp. 1
2 Ford Road
Newport Beach, California 92600
Attn: Dr. L. H. Linder, Manager
Technical Information Dept.

1 Aeroprojects, Inc. 1
310 East Rosedale Avenue
West Chester, Pennsylvania 19380
Attn: C. D. McKlune

1 Aerospace Corporation 2
P. O. Box 95085
Los Angeles, California 90045
Attn: Library-Documents

1 Allied Chemical Corporation 1
General Chemical Division
Research Lab., P. O. Box 405
Morristown, New Jersey 07960
Attn: L. J. Wiltrakis, Security Officer

1 Amcel Propulsion Company 1
Box 3049
Asheville, North Carolina 28802

1 American Cyanamid Company 1
1937 W. Main Street
Stamford, Connecticut 06902
Attn: Security Officer

IIT Research Institute 1
Technology Center
Chicago, Illinois 60616
1 Attn: C. K. Herish, Chemistry
Division

Distribution p. 4

ARO, Inc. Arnold Engrg. Dev. Center Arnold AF Station, Tennessee 37389 Attn: Dr. B.H. Goethert Director of Engrg.	1	The Dow Chemical Company Security Section Box 31 Midland, Michigan 48641 Attn: Dr. R.S. Karpiuk, 1710 Bldg.	1
Atlantic Research Corporation Shirley Highway & Edsall Road Alexandria, Virginia 22314 Attn: Library	2	E. I. duPont de Nemours & Co. Eastern Laboratory Gibbstown, New Jersey 08027 Attn: Mrs. Alice R. Steward	1
Atlantic Research Corporation Western Division 209 Easy Street El Monte, California 91731 Attn: H. Niederman	1	Esso Research & Engineering Co. Special Projects Unit P.O. Box 8 Linden, New Jersey 07036 Attn: Mr. D.L. Baeder	1
Battelle Memorial Institute 505 King Avenue Columbus, Ohio 43201 Attn: Report Library, Room 6A	1	General Dynamics/Astronautics P.O. Box 1128 San Diego, California 92112 Attn: Library & Information Services (128-00)	1
Bell Aerosystems Box 1 Buffalo, New York 14205 Attn: T. Reinhardt	1	General Electric Company Cincinnati, Ohio 45215 Attn: Technical Information Center	1
The Boeing Company Aerospace Division P.O. Box 3707 Seattle, Washington 98124 Attn: R.R. Barber, Lib. Ut. Ch.	1	Hercules Powder Company Allegany Ballistics Laboratory P.O. Box 210 Cumberland, Maryland 21501 Attn: Library	1
Chemical Propulsion Information Agency Applied Physics Laboratory 8621 Georgia Avenue Silver Spring, Maryland 20910	3	Hercules Powder Company Research Center Wilmington, Delaware 19800 Attn: Dr. Herman Skolnik, Manager Technical Information Division	1
Defense Metals Information Center Battelle Memorial Institute 505 King Avenue Columbus, Ohio 43201	1	Jet Propulsion Laboratory 4800 Oak Grove Drive Pasadena, California 91103 Attn: Library (TDS) Mr. N.E. Devereux	1
Douglas Aircraft Co., Inc. Santa Monica Division Santa Monica, California 90405 Attn: Mr. J.L. Waisman	1	Lockheed Propulsion Company P.O. Box 111 Redlands, California 92374 Attn: Miss Belle Berlad, Librarian	3

Distribution p. 5

Marquardt Corp.
16555 Saticoy Street
Box 2013 - South Annex
Van Nuys, California 91404

Martin Company
Baltimore, Maryland 21203
Attn: Science - Technology
Library - Mail 398

Minnesota Mining & Manufacturing Co. 2
900 Bush Avenue
St. Paul, Minnesota 55106
Attn: J. D. Ross
VIA: H. C. Zeman
Security Administrator

Monsanto Research Corporation
Boston Labs., Everett Station
Boston, Massachusetts 02149
Attn: Library

New York University
Dept. of Chemical Engineering
New York, New York 10053
Attn: P. F. Winternitz

North American Aviation, Inc.
Space & Information Systems Div.
12214 Lakewood Boulevard
Downey, California 90242
Attn: W. H. Morita

Rocketdyne
6633 Canoga Avenue
Canoga Park, California 91304
Attn: Library, Dept, 596-306

Rohm & Haas Company
Redstone Arsenal Research Division
Huntsville, Alabama 35808
Attn: Librarian

Space Technology Laboratory, Inc. 2
1 Space Park
Redondo Beach, California 90200
Attn: STL Tech. Lib. Doc.
Acquisitions.

1 Texaco Experiment Incorporated 1
P. O. Box 1-T
Richmond, Virginia 23202
Attn: Librarian

1 United Technology Center 1
P. O. Box 358
Sunnyvale, California 94088
Attn: Librarian

Thiokol Chemical Corporation 1
Alpha Division, Huntsville Plant
Huntsville, Alabama 35800
Attn: Technical Director

Thiokol Chemical Corporation 1
Alpha Division
Space Booster Plant
Brunswick, Georgia 31500

Thiokol Chemical Corporation 1
Elkton Division
Elkton, Maryland 21921
Attn: Librarian

Thiokol Chemical Corporation 1
Reaction Motors Division
Denville, New Jersey 07834
Attn: Librarian

Thiokol Chemical Corporation 1
Rocket Operations Center
P. O. Box 1640
Ogden, Utah 84401
Attn: Librarian

Thiokol Chemical Corporation 2
Wasatch Division
P. O. Box 524
Brigham City, Utah 84302
Attn: Library Section

Union Carbide Chemicals Co. 1
P. O. Box 8584 (Technical Center)
South Charleston, W. Virginia 25303
Attn: Dr. H. W. Schulz

United Aircraft Corporation Pratt & Whitney Fla. Res. & Dev. Ctr. P.O. Box 2691 W. Palm Beach, Florida 33402 Attn: Library	1	Chem. Research & Dev. Center FMC Corporation P.O. Box 8 Princeton, New Jersey 08540 Attn: Security Officer	1
United Aircraft Corporation Corporation Library 400 Main Street East Hartford, Connecticut 06118 Attn: Dr. David Rix	1	Ethyl Corporation P.O. Box 3091 Istrouma Branch Baton Rouge, Louisiana 70805	1
General Electric Company Apollo Support Department P.O. Box 2500 Daytona Beach, Florida 32015	1	Hynes Research Corporation 308 Bon Air Avenue Durham, North Carolina 27704	1
British Defence Staff* British Embassy 3100 Massachusetts Avenue Washington, D. C. 20008 Attn: Scientific Information Officer	4	Walter Kidde Company 675 Main Street Belleville, New Jersey 07109 Attn: Security Librarian	1
Defence Research Member * Canadian Joint Staff (W) 2450 Massachusetts Avenue Washington, D. C. 20008	4	Olin Mathieson Chemical Corp. Research Library 1-K-3 275 Winchester Avenue New Haven, Connecticut 06511 Attn: Mail Control Room Miss Laura M. Kajuti	1
Headquarters, U.S. Air Force Washington, D. C. 20330 Attn: AFRSTD	1	Pennsalt Chemicals Corporation Technological Center 900 First Avenue King of Prussia, Pennsylvania 19406	1
AFRPL (RPCL) Edwards, California 93523	1	Purdue University Lafayette, Indiana 47907 Attn: M. J. Zucrow	1
Callery Chemical Company Research & Development Callery, Pennsylvania 16024 Attn: Document Control	1	Shell Development Company 1400 53rd Street Emeryville, California 94608	1

* Reports prepared under a Department of the Air Force contract or project will be transmitted VIA:

Headquarters
Air Force Systems Command
Attn: SCS-41(3-1833)
Andrews Air Force Base
Washington, D. C. 20331

Southwest Research Institute
Department of Structural Research
8500 Culebra Road
San Antonio, Texas 78223
Attn: Dr. Robert C. DeHart, Director

Texaco, Inc.
P. O. Box 509
Beacon, New York 12508
Attn: Dr. R. E. Conary, Manager